

OFFICE OF NAVAL RESEARCH

Grant N00014-90-J-1193

TECHNICAL REPORT No. 47



Comment on "Effect on Surface Reconstruction on Stability and Reactivity of Si Clusters"

by

Brian L. Swift, Daniel A. Jelski, Donald E. Higgs, Tapio T. Rantala and Thomas F. George

Prepared for publication

in

Physical Review Letters


Departments of Chemistry and Physics State University of New York at Buffalo Buffalo, New York 14260


April 1991

Reproduction in whole or in part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale; its distribution is unlimited.







	Form Approved OMB No. 0704-0188									
1a. REPORT S	ECURITY CLASS Unclassi			1b. RESTRICTIVE MARKINGS						
22 SECURITY	CLASSIFICATIO		 	3. DISTRIBUTION/AVAILABILITY OF REPORT						
		NGRADING SCHEDU	LE	Approved for public release; distribution unlimited						
A PERFORMIN	G ORGANIZAT	ION REPORT NUMBE	R(S)	5. MONITORING ORGANIZATION REPORT NUMBER(S)						
	.0/DC/91/TI			or well and the second						
6a. NAME OF PERFORMING ORGANIZATION Depts. Chemistry & Physics State University of New York			6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION						
Froncza Buffalo	(City, State, and ak Hall, Ar o, New York	d ZIP Code) nherst Campus k 14260		7b. ADDRESS(City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Arlington, Virginia 22217						
ORGANIZA			8b. OFFICE SYMBOL (If applicable)				ION NUMBER			
	of Naval I City, State, and		ł	10. SOURCE OF FUNDING NUMBERS						
Chemist 800 N. Arlingt	ry Program Quincy States on, Virgin	n reet nia 22217		PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO	WORK UNIT ACCESSION NO			
11. TITLE (Include Security Classification) Comment on "Effect on Surface Reconstruction on Stability and Reactivity of Si Clusters"										
12 PERSONAL Brian L	12 PERSONAL AUTHOR(S) Brian L. Swift, Daniel A. Jelski, Donald E. Higgs, Tapio T. Rantala and <u>Thomas F. George</u>									
13a. TYPE OF		13b. TIME CO FROM	OVERED TO	14. DATE OF REPORT (Year, Month, Day) 15. PAGE COUNT 4						
16. SUPPLEMENTARY NOTATION Prepared for publication in the Physical Review Letters										
17.	COSATI	CODES		MS (Continue on reverse if necessary and identify by block number)						
FIELD	GROUP	SUB-GROUP	SILICON CLUSTE	ERS ISOMERS						
			45 ATOMS TIGHT-BINDING		d SYMMETRY OORDINATION	MIIMDED				
19. ABSTRACT	(Continue on	reverse if necessary	and identify by block n		OURDINATION	NUMBER	.5			
For Si ₄₅ we find two similar structures which possess full T _d symmetry of lower energy than Kaxiras'. 20. DISTRIBUTION/AVAILABILITY OF ABSTRACT 21. ABSTRACT SECURITY CLASSIFICATION										
☑ UNCLAS	SIFIED/UNLIMIT	ED 🗷 SAME AS R	PT DTIC USERS	Unclassified						
	F RESPONSIBLE David L			225. TELEPHONE ((202) 696-4	Include Area Code)	22c. OF	FICE SYMBOL			
				1 - 24 / 030-4	7.14					

Physical Review Letters, in press

Comment on "Effect on surface reconstruction on stability and reactivity of Siclusters" by Efthimios Kaxiras, Phys. Rev. Lett. 64, 551 (1990).

Brian L. Swift[#]. Daniel A. Jelski^{*} and Donald E. Higgs Department of Chemistry State University of New York, College at Fredonia Fredonia, New York 14063

Tapio T. Rantala and Thomas F. George Departments of Chemistry and Physics & Astronomy Center for Electronic and Electro-optic Materials 239 Fronczak Hall, State University of New York at Buffalo Buffalo, New York 14260

- * Author to whom correspondence should be addressed.
- # Present Address: Department of Chamistry

Hobart & William Smith Colleges

Geneva, New York 14456

+ Present Address: Department of Physics University of Oulu

SF-90570 Oulu. Finland

The structure and properties of medium-size clusters, few tens of atoms, has been a subject of several recent theoretical and experimental studies. 1-3 In particular, the question of the transition from highly-coordinated structures, typical for small clusters, to tetra-coordinated diamond structures, which is the bulk limit, has attracted much interest and created discussions in the literature, 4 although mainly based on theoretical arguments.

Kaxiras' contribution 1 to this discussion provides an interesting and well-motivated model for Si_{33} and Si_{45} clusters with a tatra-coordinated core and a bulk silicon-like reconstructed surface structure, thus suggesting that the transition region might start already at a cluster size of about 40 atoms. While this may be the case, we want to draw attention to our recent results for Si_{45} clusters, which suggest that the most stable isomers have still higher coordination numbers (from 4.0 to 4.2) than suggested by Kaxiras (about 3.1). Indeed, using classical potentials including Kaxiras', we have found two similar structures, denoted as T1 and T2, which possess full T_{d} symmetry of lower energy than Kaxiras',

We have used a variation of Tomanek and Schluter's tight-binding model 2 to check several possible isomers of Si_{45} . This was chosen because it has previously been carefully calibrated against the Si_{10} cluster, with results matching both abinitio and experimental data. We have correlated the tight-binding data with results from two classical potentials, including Kaxiras'. We find that the stability of a given isomer depends on which classical model we use, but that in general all methods qualitatively agree. In the absence of more definitive experimental data concerning Si_{45} against which the classical potentials can be calibrated, we believe that the tight-binding method is the most accurate available. The different structures are motivated by various experimental data, 2 and the results from these calculations are shown in Table 1.

Table 1. Cohesion energy per atom (in eV) for Si₄₅ isomers: "Kax" is from Ref. 1. "Benz" corresponds to seven stacked benzene-like rings with a three-atom cap, ² "Naph" to four stacked naphthalene-like rings and a five-atom cap, ² and T1 and T2 are the two new tetrahedral structures described in the text.

<u>Isomer:</u>	Kax	Benz	Naph	Т1	Т2				
Method/Potential									
Kaxiras ⁵	3.9	3.8	4.0	4.1	unstable				
Tersoff ⁵	4.0	4.0	4.3	unstable	4.5				
Tight-Binding ²	3.4	3.6	3.6	3.9	4.0				

The T1 and T2 structures are closely related. Like the Kaxiras structure, both consist of a tetrahedrally-coordinated central atom, which is in a bulk-like environment. However, the outer atoms of the cluster are not similar to a reconstructed surface. The outermost atom is hexa-coordinated, and further, the clusters consist in part of six-membered rings arranged in a tetrahedral pattern around the center. One can think of the isomers as being a bulk atom surrounded by reconstructed clusters rather than a reconstructed surface.

We suggest that these structures can account for at least some of the complicated experimental data, i.e., the relative stability of the cluster compared with the bulk surface. Further, all computational methods are consistent in that the T_d structures are of lowest energy.

Full results of our investigation and a discussion will be published elsewhere. DAJ acknowledges support from the American Chemical Society-Petroleum Research Fund, Research Corporation and SUNY Research Foundation, and TFG acknowledges support by the Office of Naval Research and the National Science Foundation under Grant CHE-9016789.

References

- 1. E. Kaxiras, Phys. Rev. Lett. 64, 551 (1990); Chem. Phys. Lett. 163, 323 (1989).
- 2. T. T. Rantala, D. A. Jelski and T. F. George, J. Cluster Sci. 1, 189 (1990), and references therein; D. Tomanek and M. A. Schlüter, Phys. Rev. B 36, 1208 (1987).
- 3. M. F. Jarrold, U. Ray and K. M. Creegan, J. Chem. Phys. 93, 224 (1990); S. Maruyama, L. R. Andersson and R. E. Smalley, J. Chem. Phys., in press; and references in these.
- J. R. Chelikowski and J. C. Phillips, Phys. Rev. Lett. 63, 1653 (1989), and references therein.
- 5. The classical potentials are from E. Kaxiras and K. C. Pandey, Phys. Rev. B 38, 12736 (1988); J. Tersoff, Phys. Rev. B 37, 6991 (1988).